



## Magna™ CL Range

Gas compressor lubricant

### Description

The Castrol Magna™ CL Range (ISO 150 - 680) are formulated with high quality mineral base oils, with the addition of friction and lubricity modifiers to increase the film strength and reduce friction. Magna CL grades are compounded oils suitable for cylinder lubrication in reciprocating type gas compressors dealing with "wet" petroleum gases.

Magna CL 1000 is formulated from selected base cylinder stocks to achieve the desirable characteristics of high flash point and oxidation stability. It possess good demulsibility, which means for the lubrication of the cylinders of high speed, totally enclosed steam engines, it does not materially reduce the demulsibility of the crankcase oil.

### Application

Magna CL 150- 680 grades are formulated for the cylinders and bearings of older type gas engines. It is blended with fatty agents (also termed "compounded"). The compounding agent provides improved load carrying properties and thus enables the oil to be used for other duties, particularly where higher loads occur or where moisture is present.

Magna CL 1000 is designed for lubrication of steam engine cylinders and valves. It is also suitable for other purposes, such as the lubrication of heavily loaded slow-moving bearings and gears. It is also suitable for condensing engines using high pressure steam up to 200psi and superheat up to 345°C/653°F.

Higher viscosity products from Magna CL range can also be used in worm gearboxes.

# Typical Characteristics

Name	Method	Units	Magna CL 150	Magna CL 220	Magna CL 320	Magna CL 460	Magna CL 680	Magna CL 1000
Appearance	Visual	-	Straw Viscous Liquid	Brown Viscous Liquid	Brown Viscous Liquid	Dark Viscous Liquid	Dark Viscous Liquid	Dark Viscous Liquid
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m <sup>3</sup>	889	889	890	910	920	940
Kinematic Viscosity at 40°C / 104°F	ISO 3104 / ASTM D445	mm <sup>2</sup> /s	150	220	320	460	680	1000
Kinematic Viscosity at 100°C/ 212°F	ISO 3104 / ASTM D445	mm <sup>2</sup> /s	13.6	17.7	23.2	28.7	38	44
Viscosity Index	ISO 2909 / ASTM D2270	-	83	86	86	88	88	80
Flash Point - open cup method	ISO 2592 / ASTM D92	°C/°F	243 / 469	255 / 491	261 / 502	267 / 513	267 / 513	-
Flash Point - closed cup method	ISO 2719 / ASTM D93	°C/°F	-	-	-	-	-	260 / 500
Pour Point	ISO 3016 / ASTM 97	°C/°F	-9 / 16	-9 / 16	-6 / 21	-3 / 27	-3 / 27	-

Subject to usual manufacturing tolerances.

20 Apr 2020

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>